

Things to consider when choosing a hose

- This chemical resistance table indicates if the **inner tube** of hose is **resistant** to specific materials/chemicals throughout different temperatures.
- Some materials/chemicals can in contact with the hose change colours, if it's important that the colours stay unchanged, we recommend that you to contact us.
- For foodstuff the table only indicates wheather the innertube is **resistant** to the product. This does'nt automaticly significates that the innertube is foodstuff **approved**.
- Phenomenon such as abrasion, friction and mechanical influence can increase the chemical's aggresivity and therefore decrease the lifetime of the hose.
- All rates in table are exclusivly for the **transport** of media.
- NB. Materials can change colours in contact with other kinds of materials.

Outer stress is always an important factor. Therefore this resistance table should be considered as a indication and not a guarantee.

International material codes

Rubber:

- NR** - Natural rubber
- SBR** - Styrene butadiene rubber
- NBR** - Nitrile rubber
- EPDM** - Ethylene-propylene rubber
- IIR** - Butyl rubber
- CR** - Chloroprene rubber (Neopren)
- CSM** - Chlorosulfonated polyethylene rubber (Hypalon)

Plastic:

- P.T.F.E.** - Polytetraflouro ethylene (Teflon®)
- PP** - Polypropylene
- UPE** - Ultra high molekular weight polyethylene
- XLPE** - Cross linked polyethylene (PEX)
- PU** - Polyurethane
- PE** - Polyester platsic (Elastomer)
- PA** - Polyamide (Nylon)
- PVC** - Polyvinylchloride

How to read the table

Fitness grade:

- A - Good to excelent**
- B - Acceptable for limited use**
- C - Not suitable**

	UPE		P.T.F.E.		EPDM		
	25	70	25	70	25	70	100
Aceton	A		A	A	A	A	
Acetonitil	A		A	C	C	C	C
Acetonitril	B	B	A	A	B		

International material codes

Chemical substance temperature in °C

Chemical substance in alfabetic order

Fitness grade divided in temperature areas

	NR		SBR		NBR		EPDM		IIR		CR		CSM		FEP		pp		UPe		PEX		PA		PE		PU		PVC	
	25	70	25	70	25	70	25	70	100	25	70	90	25	70	90	25	70	25	70	25	70	25	70	25	70	25	70	25	70	
Bromine Water	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	A	A								
Bromobenzene	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Bromochloroethane	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Bromochloromethane	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Bromoform	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Bromotoluene	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butadiene Monomer	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butaldehyde	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butane	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butanol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A							
Butanone	C	C	C	C	C	C	C	C	C	A	C	C	C	C	C	C	A	A	C	C	B	B								
Butter	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Acetate	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Acetoacetate	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Acrylate	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Alcohol	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A	A							
Butyl Benzene	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Benzoate			C	C	C	C	C	C	C	A	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Bromide	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Butyrate	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Carbitol	C	C	C	C	C	C	C	C	C	A	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Chloride	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Ether	C	C			C	C	C	C	C		C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Mercaptan	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Methacrylate	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Oleate	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Phenol	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Phthalate	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butyl Stearate	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butylamine	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butylene	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C	A	A	C	C	B	B								
Butylethyl Acetaldehyde	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								
Butylethyl Ether	C	C	C	C	C	C	C	C	C	A	C	C	C	C	C	C	A	A	C	C	B	B								
Butylmonobutyl Ether	C	C	C	C	C	C	C	C	C	A	C	C	C	C	C	C	A	A	C	C	B	B								
Butylsebacate	C	C	C	C	C	C	C	C	C	A	C	C	C	C	C	C	A	A	C	C	B	B								
Butyraldehyde	C																													
Butyric Acid	C	C	C	C	C	C	C	C	C	B	C	C	C	C	C	C	A	A	C	C	B	B								

	NR		SBR		NBR		EPDM		IIR		CR		CSM			FEP		pp		UPE		PEX		PA		PE		PU		PVC				
	25	70	25	70	25	70	25	70	25	70	25	70	25	70	90	25	70	25	70	25	70	25	70	25	70	25	70	25	70	25	70	25	70	
Creosols	C	C					C	C	C								A	A	C	C	A	A	A	B	C									
Creosote Oil	C	C	C	C							C	C	C	C	C		A	A	C	C	A	A	B											
Creosotes	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A	A											
Crotonic aldehyde	B		B		A		A		A		A		A				A	A			A	A												
Cryolite 10%	A		A		B		A		A		A		A				A	A			A	A												
Cumene	C	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A												
Cuprous Cyanide	A				A		A		A		A		A				A	A			A	A												
Cyclohexanol	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Cyclohexane	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Cyclohexanol	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Cyclohexanone	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Cyclohexylamine	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Cymene	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Decahydronaphthalene	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Decaline	C	C			C	C	C	C	C								A	A			A	A												
Decane	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Developer	A		B		A		A		B		A		A				A	A			A	A												
Dextrine	A		A		A		A		A		A		A				A	A			A	A												
Dextrose	A	A	A	A	A	A	A	A	A	A	A	A	A	A			A	A			A	A												
Diamyl Phthalate	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Dibenzyl Ether (Benzyl ether)	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Dibenzyl sebacate	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Dibromodifluoromethane	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Dibromoethylbenzene	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Dibutyl Ketone	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Dibutyl Phthalate DBP	C	C	C	C	C	C	C	C	C	C	C	C	C	C		A	A			A	A													
Dibutylamine	C	C			C	C	C	C									A	A			A	A												
Dibutylsebacate	C	C	C	C	C	C	C	C	B		C	C	C	C			A	A			A	A												
Dichloroacetic Acid 100%	B		C	C	C	C	C		C	C	C	B					A	A			A	A												
Dichloroacetic Acid 50%	B		C	C	C	C			C	C	B						A	A			A	A												
Dichlorobenzene	C	C	C	C	C	C	C		C	C	C	C	C	C			A	A			A	A												
Dichlorobutane	C	C	C	C	C	C	C	C	C	C	C	C	C	C			A	A			A	A												
Dichlorobutylene	C	C	C	C	C	C	C	C	C	C	C	C	C	C			A	A			A	A												
Dichlorodifluoromethane (Freon 12)	B		A		A		A		B		A		A				A	A			A	A												
Dichloroethane	C	C			C	C	C	C									A	A			A	A												

D

	NR		SBR		NBR		EPDM		IIR		CR		CSM			FEP		pp		UPe		PEX		PA		PE		PU		PVC		
	25	70	25	70	25	70	25	70	100	25	70	90	25	70	25	70	90	25	70	25	70	25	70	25	70	25	70	25	70	25	70	
Urea	A		A		B		B						A		A				A	A	A	A	A								A	
Uric Acid	A		A		A																A	A	A									
Urine	A		A		A		A						A		A				A	A	A	A	A									
V																																
Varnish (Depend on solvents)																																
Vaseline	C	C	C	C	C	C	C	C					B		A				A	A	A	A	A		A							
Vegetable & Animal Oils	C	C	C	C	A	A	A						C	C	C	C	C	C	C	C	A	A	A									
Vegetable Fat	C	C	C	C	A	A	C	C					B		B				A	A	A	A	A									
Vegetable Oil	C	C	C	C	B		C	C					C	C	C	C	C	C	C	C	A	A	A									
Vinegar	B	C	C	C	A	C	A	C					A	B	B	C	C	C	A	A	A	A	A		B							
Vinylacetate	C	C	C	C	C	C	C	C					B		C	C	C	C	A	A	A	A	A									
Vinylchloride	C	C	C	C	C	C	C	C					C	C	C	C	C	C	C	C	A	A	A									
Vinylcyanide	B		B		C	C	C	C					C	C	C	C	C	C	C	C	A	A	A									
Vinylfluoride	C	C	C	C	C	C	C	C					C	C	C	C	C	C	C	C	A	A	A									
Vinylmethacrylate	C	C	C	C	C	C	C	C					C	C	C	C	C	C	A	A	A	A	A									
Vinylmethanol	A				B		A						A		A				A	A	A	A	A									
Vinylacetylene	B		B		A		A						A		C	C	C	C	C	C	A	A	A									
Vinylether	C	C	C	C	B		C	C					C	C	B				A	A	A	A	A									
Vinylidene chloride	C	C	C	C	C	C	C	C					C	C	C	C	C	C	C	C	A	A	A									
W																																
Water	A	A	A	A	A	A	A	A					A	A	A	A	A	A	A	A	A	A	A		A							
White Spirit	C	C	C	C	A		C	C					C	C	C	C	C	C	C	C	A	A	A									
Wine	A	A	A	A	A		A						C	C	C	C	C	C	A	A	A	A	A									
X																																
Xenon	A	A	A	A	A	A	A	A					A		A	A	A	A	A	A	A	A	A									
Xylene	C	C	C	C	C	C	C	C					C	C	C	C	C	C	C	C	A	A	A		A		B					
Xylenol	C	C	C	C	C	C	C	C					C	C	C	C	C	C	C	C	A	A	A									
Xylidine	C	C	C	C	C	C	C	C					C	C	C	C	C	C	C	C	A	A	A									
Y																																
Yeast	A		A		A		A						A		A				A	A	A	A	A									
Z																																
Zeolite	A	A	A	A	A	A	A	A					A	A	A	A	A	A	A	A	A	A	A									
Zinc Acetate	B		C	C	B		A						A	A	A	B			A	A	A	A	A									
Zinc chloride	B		B		B		A						B		A				A	A	A	A	A									
Zinc Sulphate	B	B	B	B	A	A	A	A					A	A	A	A	A	A	A	A	A	A	A		B		A					